

Products	Curing (°C)	Coloured series	Elasticity	Pigmentable	Transfer
Transparents	NEUTRO	160°	•		•
	FCP (QUADRICROMIA)	160°	•	•	•
Opagues	COLORI	130°	•	•	•
	FLUO	160°	•	•	
	BLOCK GREY	160°		•	•
	B.T. TC (COPRENTE)	160°		•	•
	MATT	160°		•	•
Special Effects	3D				
	FOAM	150° - 160°		•	•
	BASE TRASPARENTE EL	160°		•	•
	BASE TRASPARENTE BS	160°		•	•
	BASE TRASPARENTE AS	160°		•	•
	ORO RICCO	160°		•	•
	ARGENTO	160°		•	•
	PERLA	160°	•	•	•
	Adhesives				
	BASE TRASPARENTE TR	110°-120°		•	•
BASE TRASPARENTE GD	110°-120°		•	•	

PLAST+ WHITES

LEGEND 1=LOW 2=SUFFICIENT 3=QUITE GOOD 4=GOOD 5=EXCELLENT

Products	Screen Printing	Transfer	Elastic	Non Elastic	Background	Phthalate Free	Heavy Metal Free	Curing (°C)	Printability	Opacity	No - Tacking	Drying Time Flash Curing	Touch	No - Bleeding	Suggested screen (Yarns/cm)	Washing Resistance (°C)
BIANCO ECO	•	•	•	•	•	•	•	160°	5	4	4	5	4	3	90	60
BIANCO HQ	•	•	•	•	•	•	•	160°	4	5	4	5	5	3	90	60
BIANCO EL	•	•	•	•	•	•	•	160°	4	4	3	3	3	1	70	60
BIANCO LF	•	•	•	•	•	•	•	130°	4	5	5	5	3	3	90	60
BIANCO FLASH	•	•	•	•	•	•	•	160°	5	4	4	5	4	3	90	60

PLAST+ AUXILIARIES

Products	Plast base HT (Increase elasticity and softness)	Lubrilac plast (Reduce ink viscosity)	Plast thinner (Reduce ink viscosity)	Plastfoam (Puff base)	Plast matt (Matting agent)	Plast base TR (Hot-split transfer)
COLORI	5% - 10%	5%	5% - 10%	40% - 70%	20% - 40%	20% - 40%
FLUO	5% - 10%	5%	5% - 10%	40% - 70%		20% - 40%
FCP (QUADRICROMIA)	5% - 10%	5%	5% - 10%			
BLOCK GREY		5%	5% - 10%			
FOAM	5%	5%	5% - 10%			20% - 40%
BASE TRASPARENTE EL		5%	5% - 10%			
BASE TRASPARENTE BS		5%	5% - 10%			
BASE TRASPARENTE AS		5%	5% - 10%			
BASE TRASPARENTE TR	5% - 10%	5%	5% - 10%	40% - 70%		
ORO RICCO	5% - 10%	5%	5% - 10%			20% - 40%
ARGENTO	5% - 10%	5%	5% - 10%			20% - 40%
PERLA	5% - 10%	5%	5% - 10%			20% - 40%